

Client: Harrison's Trim Supplies
Gladstone House
Victoria Terrace
Cleckheaton
West Yorkshire
BD19 3BH

Entry No: 67863

Date received: 27/11/2014

Client's Description: Sample of Easyliner

TEST REPORT

Test Required: Flammability
Pre-treatment: None
Conditioning: A minimum of 24 hours at 50 +/- 5% Relative Humidity, 21 +/- 1°C
Method of Test: FMVSS 302
Date of Test: 04/12/2014

Results:

	Burning Rate (mm/min)
Specimen 1	85
Specimen 2	83
Specimen 3	84
Specimen 4	87
Specimen 5	76

Comments

On the basis of the tests carried out this sample meets the requirements of FMVSS 302.

-----End of Document-----

This is hereby certified to be a correct return of the tests made of the items referred to herein.



D. Brockbank.
Materials Testing Manager
9th December 2014

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- ❖ Test marked (*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ❖ This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

